

ANQA POXY TC-300SF

Solvent Free, Epoxy Flooring Top Coat



DESCRIPTION:

ANQA POXY TC-300SF is a solvent-free, 2K epoxy flooring top coat system, for technical flooring and high mechanical features required flooring.

ADVANTAGES:

- Easy to clean and smooth glossy, semi-gloss, or matte flooring that does not induce bacterial or fungal growth.
- Excellent chemical and mechanical resistance.
- Non-toxic.
- Exhibits good mechanical properties.
- Easy application.

APPLICATION AREAS:

- Showrooms.
- Warehouses.
- Car parks.
- Soft drink, beverage, and food processing and production plants.
- Dairies production areas.
- Maintenance & car wash shops' floors

APPLICATION METHOD:

Surfaces must be solid and cleaned of any loose particles, grease, and oil.

Use **ANQA POXY** repairing material to ensure proper floor preparation and readiness for coating.

Assure the compressive strength of the concrete floor before applying the product (at least 25 N/mm²)

Ensure the concrete relative humidity is less than 80%. Relative humidity can be measured using a hygrometer. Concrete relative humidity should be less than 80% (after 28 days old concrete)

Primer Application: A primer must be applied over porous and concrete surfaces; **POXY PR-400SF** is recommended. **Mixing:** Mix **POXY TC-300SF** (2 parts: resin + hardener) according to the ratio specified on the packaging. **Application:** Use a mechanical mixer to ensure uniform consistency and proper color distribution.

Coating: Coat using the appropriate tools, such as a brush, knife, notched trowel, spike roller, and spike shoes. Ensure the required quantity is mixed, and avoid using the mixed material (resin + hardener) after 1 hour (pot life).

COVERAGE:

2.3 sq.m/kg @400 micron coat

HEALTH & SAFTEY:

Skin & Eye contact: Avoid prolonged contact with eyes and skin. For detailed information, refer to the relevant material safety data sheet.

Cleaning: use **ANQA-POXY SOLV**. remover solvent or any suitable solvent f to clean tools.

SHELF LIFE:

12 months for unopened containers; use older stock first.

WARNINGS:

- Do not overcoat on other flooring systems. Refer to our technical department for further instructions and recommendations before proceeding.
- ANQA POXY TC-300SF is not color stable if used on exposed areas and direct sunlight can affect the color stability.

ANQA POXY TC-300SF

Solvent Free, Epoxy Flooring Top Coat



🔗 www.anqa.com.sa 🛛 🕱 @anqa_com_sa 🔘 f @anqa.com.sa

TECHNICAL SPECIFICATIONS:

SPECIFICATIONS	RESULTS
Appearance	Thick colored paint
Water permeability	≈ Zero
Solid Content (%) (Mixture)	100%
Specific gravity	${\approx}1.50~\text{kg/L}\pm0.1$
Pot life	40-60 minutes @ 25°C
Curing Time:	7 days
Dust Dry @30°C:	2 hours.
Hard Dry @30°C:	8 hours.
Mixing ratio	4:1 (resin:hardener)
VOC Content (ASTM D3690)	≤ 9 g/kg
Compressive strength:	
BS 6319-2	≥ 70 MPa at 7 days
Flexural strength:	
BS 6319-3	≥ 30MPa at 7 days